



REVIEW ARTICLE

Chemical Decellularization Methods and Its Effects on Extracellular Matrix

Amir Hossein Akbari Zahmati^{1*}, Reza Alipoor², Arash Rezaei Shahmirzadi³, Vahid Khor⁴, Mohammad Mahdi Abolhasani⁵

¹Student Research Committee, Dental Faculty, Golestan University of Medical Sciences, Gorgan, Iran

²Student Research Committee, Fasa University of Medical Sciences, Fasa, Iran

³Student Research Committee, Medicine Faculty, Golestan University of Medical Sciences, Gorgan, Iran

⁴Ischemic Disorders Research Center, Golestan University of Medical Sciences, Gorgan, Iran

⁵School of Medicine, Mashhad Islamic Azad University, Mashhad, Iran

Correspond Author: Amir Hossein Akbari Zahmati, E-mail: amirakbarizahmati74@gmail.com

ARTICLE INFO

Article history

Received: May 6, 2017

Accepted: Jun 7, 2017

Published: Aug 4, 2017

Volume: 2

Issue: 3

Conflicts of interest: None

Funding: None

Key words

Extracellular Matrix,
Chemical Methods,
Decellularization

ABSTRACT

Background: Extracellular matrix (ECM) produced by tissue decellularization processes as a biological scaffold due to its unique properties compared to other scaffolds for migration and implantation of stem cells have been used successfully in the field of tissue engineering and regenerative medicine in the last years. The objective of this manuscript was to provide an overview of the chemical decellularization methods, evaluation of decellularized ECM and the potential effect of the chemical decellularization agents on the biochemical composition.

Methods: We searched in Google Scholar, PubMed, Scopus, and Science Direct. The literature search was done by using the following keywords: "ECM, biologic scaffold, decellularization, chemical methods, tissue engineering." We selected articles have been published from 2000 to 2016, and 15 full texts and 97 abstracts were reviewed. **Results:** Employing an optimization method to minimize damage to the ECM ultrastructure as for a result of the lack of reduction in mechanical properties and also the preservation of essential proteins such as laminin, fibronectin, Glycosaminoglycans (GAGs), growth factor is required. Various methods include chemical, physical and enzymatic technics were studied. However, on each of these methods can have undesirable effects on ECM. **Conclusion:** It is suggested that instead of the Sodium dodecyl sulfate (SDS) which have high strength degradation, we can use zwitterionic separately or in combination with SDS. Tributyl phosphate (TBP) due to its unique properties can be used in decellularization process.

INTRODUCTION

Using extracellular matrices (ECM), as a bioscaffold for tissue regeneration has been welcomed in the past few years, therefore, in recent years (1-7), various methods from different tissues have been tested to produce the healthy ECM. So far, ECM from various tissues has been made, and efforts have been put to use some of these biological scaffolds in tissue engineering and regeneration of organs. As regards tissues that have been used to produce ECM, heart (8-11), blood vessels (12,13), skin (14), nerve (15), skeletal muscle (16), tendon (17), small intestine (18), oral mucosa (19-21), jawbone and teeth (22-24), sinusoidal mucosa (25), liver (26) and lung (27) can be noted. The unique structure of the ECM causes the cells with tissue repair properties, to multiply within the ECM. Using ECM reduces the immune responses, thereupon occasion enhances the

success rate of tissue transplantation and lack of tissue rejection. Also, ECM contains factors for cell growth and proliferation, as well as containing non-collagenous proteins potentially, including laminin and fibronectin to increase the adhesion of cells to the scaffold (28) as well glycosaminoglycans (GAGs). Various methods, including physical, chemical and biological technics are used throughout the process of decellularization; however, the most effective decellularization process results from the combination of physical, chemical, and biological methods. Other important factors such as tissue type, density, and tissue thickness are also involved (5). The aim of this study was reviewing the chemical methods that are used in decellularization, evaluation of there, and effects of each chemical method on biochemical compounds, structural and mechanical behavior of ECM.

CHEMICAL METHODS

Using chemical methods facilitates decellularization which includes chemical agents, acid and bases, detergents, alcohols, hypotonic and hypertonic solutions.

Acid and Base

Acids and bases cause nucleic acid decomposition and hydrolysis of cytoplasmic components (1,29). Acids and Bases that are used in decellularization protocols are acetic acid (30), peracetic acid (PAA), hydrochloric acid, sulfuric acid, ammonium hydroxide, calcium hydroxide, and sodium hydroxide (3).

PAA is commonly used throughout the process of decellularization (31). It can maintain growth factors such as growth factor β , VEGF, laminin and fibronectin, which are involved in adhesion of cells to the ECM (32-35) and have been established to have no adverse effect on the mechanical properties of ECM (36).

It also has been disinfecting, and microbial enzymes oxidizing properties (37,38). PAA concentration of 0.1% has been successfully used in decellularization of small intestine submucosa (SIS) and urinary bladder matrix (UBM) (39,40). One of the problems with using acids throughout the process of decellularization is the deletion GAG from the ECM (41).

Bases are mostly used to remove hair from skin samples before starting the process of decellularization (42,43); however, the damaging effects of bases on the ECM and its collagenous protein constituents, reduce the mechanical properties of ECM and removes the growth factors from the ECM (44).

Hypotonic and Hypertonic Solutions

Hypotonic and hypertonic solutions cause cell lysis by inducing osmotic shock in the tissue and breakdown of the cell membrane in tissues or organs (44-48). Hypertonic solutions have the ability to separate protein from DNA (49). One of the reasons for using hypotonic solutions is a minimal change in the structure of the ECM (50). Moreover, hypotonic and hypertonic solutions are used for washing cell debris, but they are not able to clean and remove cell debris from the tissues entirely (51-53).

Alcohols

Glycerol is one of the most commonly used alcohols in decellularization which causes cell lysis, dehydration (54), and effectively removes lipids. It has more detergency and decomposing capabilities compared to lipase (42,55). Methanol along with chloroform are used as the other compounds for delipidation are (54). One of the problems of using methanol and ethanol to fix tissues is protein precipitation. Therefore, one should be cautious in using methanol and ethanol in the process of decellularization because it may damage the protein structure of ECM and affect its mechanical properties (43,56-60). Lipid occasion calcification, so alcohol is considered as an anti-calcifying agent (56,61).

Detergents

Detergents are amphipathic molecules with a polar and aquaphobic head that can dissolve hydrophobic compounds in water. Detergents are used in 2-dimensional electrophoresis in addition to being used in the process of decellularization (62). Detergents are classified based on their polar head into three categories as follows: ionic, non-ionic and ion-dipole.

Ionic Detergent

Ionic detergents are effectively used in removal and dissolution of membrane proteins and DNA associated proteins (63). Sodium dodecyl sulfate (SDS) is widely used in the process of decellularization (63). In comparison with other detergents, SDS has more effectiveness to the removal of the cell debris such as nuclear and cytoplasmic compounds from dense and thick tissues (e.g., heart) (9,64). Hence, it is the most commonly used detergent in decellularization (47,59,65). Although SDS cleaning power is stronger than many other detergents, it also has more destructive effects compared with other detergents (66-69). A disadvantage of using SDS as a detergent is reducing the amount of GAG and growth factors from the ECM (43). Due to the strong tendency of SDS toward protein, it can disrupt protein-protein interactions. Thus it may have a role in the loss of collagen integrity and change in the ECM structure (70-72). Using SDS in different concentrations leads to various injuries on ECM levels (5). Previous studies on the vein and gums were examined various concentrations of SDS that revealed optimized concentration with the highest level of decellularization (29,72).

The destruction level of a detergent depends on its type, detergent and fabric duration of exposure, type of tissue and age of the tissue donor (43,73). Sodium deoxycholate is another ionic detergent which used in decellularization, but it has more destructive power compared to SDS, and it is typically used in combination with bipolar detergents (74,75). Triton X-200, similar to SDS and sodium deoxycholate is used as an ionic detergent in the process of decellularization (76-80).

Non-ionic Detergents

Non-ionic detergents have lower destructive effects on the structure of ECM. However, detergents are widely used in the process of decellularization. Non-ionic detergents can break down lipid-lipid bonds, but cannot destroy the protein-protein bonds (81). Triton X-100 is used as a non-ionic detergent in decellularization. This detergent has been used in decellularization of tissues such as liver (82-84), pericardium (85), lung (7,86,87), gum (88) and skin (89).

This compound has biodegradable properties and a high ability to destroy and remove cells from the surface of ECM (90) and provide the conditions for the growth of cells. Some studies revealed the effects of Triton X-100 on decellularization of blood vessels, tendons, ligaments, myocardium and aortic walls that no success was seen, while it has been successfully used in decellularization of heart

valves (47,48,91). These researches show that the use of Triton X-100 in decellularization has both said results. Many studies regarding decellularization have demonstrated that Triton X-100 eliminates GAG from ECM surface (92). However, in a study on decellularization of anterior cruciate ligament (ACL), it was shown that this detergent does not have any harmful effects on GAG levels of ECM surface (47). Triton X-100 is known as the best detergent in the process of delipidation and compared to SDS, and other detergents such as sodium doxycycline lipase and even lipase have shown a much better performance (93,94).

Bipolar Detergents

Bipolar detergents have the properties of both ionic and non-ionic detergents that are mostly used in decellularization of thin tissues (95,96). Bipolar detergents such as CHAPS, sulfobetaine-10, and sulfobetaine-16 are used in the process of decellularization. For example, CHAPS were used in decellularization of blood vessels (48) and sulfobetaine-10, and 16 sulfobetaine were applied in decellularization of nerves (15).

Chelates

These compounds are tightly combined with an ion. EDTA and EGTA are examples of these chemical compounds that are used in the process of decellularization. These chemical's compositions destruct cell connections to collagen and fibronectin by separating ions such as Ca^{2+} and Mg^{2+} (97-100). Chelating agents are usually used in combination with enzymes such as trypsin (9,52,101-103) or detergents (9,101) and do not have any application on its own (104). EDTA in the long term reduces the mechanical properties of the scaffold (105).

Organic Solvents

Tributyl phosphate (TBP) is one of the most widely used organic solvents in the process of decellularization. TBP performs as a destructor of the protein structure. These chemical's compositions also have anti-viral properties. Using organic solvents such as TBP is also a suitable alternative for ionic and non-ionic detergents for thick tissues. One of the advantages of TBP compared to others is the minimal damage that may cause to the mechanical properties of ECM. It is used in decellularization of dense tissues such as tendons and ligaments. Therefore, further studies are required in this field (17,47).

Effects of Decellularization on ECM

The process of decellularization may have some adverse effects on the ECM, including reduction of collagenous and non-collagenous proteins such as laminin, fibronectin, glycosaminoglycans. It also removes water molecules attached to it and thereby reduces the elasticity of tissue. Removal of collagenous proteins as well decreases the mechanical properties of ECM (17,47).

Evaluation of Decellularization Process

For standard assessment of a method of tissue decellularization, histological analysis, determination of the amount of DNA, GAG, biomechanical analysis, continuity of collagenous scaffolds, non-collagenous proteins are required.

Several methods are available to identify the effects of decellularization on the removal of cellular materials and on the ECM itself, for instance, hematoxylin-eosin staining to the investigation of histological analysis and Movat's Pentachrome staining for detecting the presence of cytoplasmic and ECM molecules.

A specific quantitative amount of cellular materials has not been determined in the process of decellularization although it is possible to overcome the problem that based on laboratory research findings as well as in vivo responses to the reconstructed models. For instance, the amount of DNA in every mg of ECM should not be less than 50ng.

The amount of DNA fragments should be less than 200 bp, and nuclear materials should also stay undetected in 4', 6-diamidino-2-phenylindole (DAPI) or hematoxylin-eosin staining because DNA directly causes an immune response in the host body (1,106,107). DNA density can also be identified by using fluorometric stainings such as Hoechst (108-110). DNA is present everywhere in the tissue and could be easily detected and used as an overall indicator for measuring the elimination of cell debris from the surface of the ECM (111). Immunohistochemistry is used as a staining for detecting the presence of non-collagenous proteins such as collagen, laminin, fibronectin, glucose, GAG, actin, and myosin (47). Pyrrolone, a major amino acid in the ECM structure is used as a standard indicator in assessing the amount of protein degradations such as collagen and elastin (109,112). Evaluation of the effects of decellularization on the mechanical properties of ECM and cell debris on the ECM after the process has always been one of the main issues in this process. In previous studies, the effects of different detergents on the ECM were assessed, and it was demonstrated that these detergents cause damage to the ECM collagen and therefore, reduce the mechanical properties.

However, there are also exceptions, in studies on the use of Triton X-100 in the process of decellularization of ACL, it was revealed that Triton X-100 have not any destructive effects on ECM collagen (17)

CONCLUSION

The use of ECM as a biological scaffold in the past few years has been studied. Decellularization of the trachea and successful deployment of its ECM in tracheal reconstruction has shown an excellent prospect in the field of tissue engineering by using bio-scaffolds. In order to obtain a healthy ECM, it is necessary to implement an optimized method with the lowest level of damage to the structure of ECM and lack of decrease in its mechanical properties as well as preserving important proteins such as laminin, fibronectin, GAGs and growth factors. A suitable protocol should also be able to clear nuclear materials and cell debris from the ECM. The presence of these materials in terms of in-vivo conditions leads to host's im-

immune response. However, no protocol has been recorded with 100% efficiency. This efficiency depends on some factors, including the type of tissue, type of decellularization method as well as the composition of these methods. As mentioned earlier, a complete decellularization requires a combination of all three biological, chemical and physical methods. In the process of decellularization, detergents such as SDS play a key role. However, these detergents cause damage to collagenous and non-collagenous proteins, GAGs and growth factors. It also causes irreparable damage to the ECM structure. For this reason, it can be suggested to use di-ionic detergents (bipolar) that are less destructive compared to SDS. Even bipolar detergents could be used in combination with a low concentration of SDS for increased cleaning power of this cellular detergent. Hence, this review can help clinicians to select the appropriate method in decellularization processing for achieving ECM as a scaffold in organ transplantation processes.

ACKNOWLEDGEMENT

We thank Department of Ischemic Disorders Research Center of Golestan University of Medical Sciences for supporting us.

AUTHORS CONTRIBUTION

Amir Hossein Akbari Zahmati, Reza Alipoor, Arash rezaei shahmirzadi, Vahid Khorrami and Mohammad Mahdi Abolhasani gathering data and Amir Hossein Akbari Zahmati Analyzed Data, wrote primary draft, revised and submitted it.

REFERENCES

1. Crapo PM, Gilbert TW, Badylak SF. An overview of tissue and whole organ decellularization processes. *Biomaterials*. 2011;32(12):3233-43.
2. Gilbert TW. Strategies for tissue and organ decellularization. *Journal of cellular biochemistry*. 2012;113(7):2217-22.
3. Gilbert TW, Sellaro TL, Badylak SF. Decellularization of tissues and organs. *Biomaterials*. 2006;27(19):3675-83.
4. Hrebikova H, Diaz D, Mokry J. Chemical decellularization: a promising approach for preparation of extracellular matrix. *Biomed Pap Med Fac Univ Palacky Olomouc Czech Repub*. 2015;159(1):12-7.
5. Patnaik SS, Wang B, Weed B, Wertheim JA, Liao J. Decellularized scaffolds: concepts, methodologies, and applications in cardiac tissue engineering and whole-organ regeneration. *Tissue Regeneration: Where Nanostructure Meets Biology Singapore: World Scientific*. 2014:77-124.
6. Shafiq M, Jung Y, Kim SH. Insight on stem cell preconditioning and instructive biomaterials to enhance cell adhesion, retention, and engraftment for tissue repair. *Biomaterials*. 2016;90:85-115.
7. Song JJ, Ott HC. Organ engineering based on decellularized matrix scaffolds. *Trends in molecular medicine*. 2011;17(8):424-32.
8. Ott HC, Matthiesen TS, Goh S-K, Black LD, Kren SM, Netoff TI, et al. Perfusion-decellularized matrix: using nature's platform to engineer a bioartificial heart. *Nature medicine*. 2008;14(2):213-21.
9. Wainwright JM, Czajka CA, Patel UB, Freytes DO, Tobita K, Gilbert TW, et al. Preparation of cardiac extracellular matrix from an intact porcine heart. *Tissue Engineering Part C: Methods*. 2009;16(3):525-32.
10. Costa KD. Decellularized Scaffold Hydrogel Materials for MI Treatment. *Journal of the American College of Cardiology*. 2016;67(9).
11. Akhyari P, Aubin H, Gwanmesia P, Barth M, Hoffmann S, Huelsmann J, et al. The quest for an optimized protocol for whole-heart decellularization: a comparison of three popular and a novel decellularization technique and their diverse effects on crucial extracellular matrix qualities. *Tissue Engineering Part C: Methods*. 2011;17(9):915-26.
12. Hodonsky C, Mundada L, Wang S, Witt R, Raff G, Kaushal S, et al. Effects of scaffold material used in cardiovascular surgery on mesenchymal stem cells and cardiac progenitor cells. *The Annals of thoracic surgery*. 2015;99(2):605-11.
13. Gui L, Niklason LE. Vascular tissue engineering: building perfusable vasculature for implantation. *Current opinion in chemical engineering*. 2014;3:68-74.
14. Parker DM, Armstrong PJ, Frizzi JD, North JH. Porcine dermal collagen (Permacol) for abdominal wall reconstruction. *Current surgery*. 2006;63(4):255-8.
15. Hudson TW, Liu SY, Schmidt CE. Engineering an improved acellular nerve graft via optimized chemical processing. *Tissue engineering*. 2004;10(9-10):1346-58.
16. Borschel GH, Dennis RG, Kuzon Jr WM. Contractile skeletal muscle tissue-engineered on an acellular scaffold. *Plastic and reconstructive surgery*. 2004;113(2):595-602.
17. Docheva D, Müller SA, Majewski M, Evans CH. Biologics for tendon repair. *Advanced drug delivery reviews*. 2015;84:222-39.
18. Lantz GC, Badylak SF, Coffey AC, Geddes LA, Blevins WE. Small intestinal submucosa as a small-diameter arterial graft in the dog. *Journal of Investigative Surgery*. 1990;3(3):217-27.
19. Chai WL, Moharamzadeh K, Brook IM, Emanuelsson L, Palmquist A, van Noort R. Development of a novel model for the investigation of implant-soft tissue interface. *Journal of periodontology*. 2010;81(8):1187-95.
20. Moharamzadeh K, Brook I, Van Noort R, Scutt A, Thornhill M. Tissue-engineered oral mucosa: a review of the scientific literature. *Journal of Dental Research*. 2007;86(2):115-24.
21. Mohammadi M, Shokrgozar MA, Mofid R. Culture of human gingival fibroblasts on a biodegradable scaffold and evaluation of its effect on attached gingiva: A randomized, controlled pilot study. *Journal of periodontology*. 2007;78(10):1897-903.
22. Tabatabaei F, Motamedian S, Gholipour F, Khosraviani K, Khojasteh A. Craniomaxillofacial bone

- engineering by scaffolds loaded with stem cells: A systematic review. *J Dent Sch.* 2012;30(2):115-31.
23. Lee MK, DeConde AS, Lee M, Walther CM, Sepahdari AR, Elashoff D, et al. Biomimetic scaffolds facilitate healing of critical-sized segmental mandibular defects. *American journal of otolaryngology.* 2015;36(1):1-6.
 24. Motamedian FSTSR, Khosraviani FGK, Khojasteh A. Craniomaxillofacial Bone Engineering by Scaffolds Loaded with Stem Cells: A Systematic Review. *Journal Dental School.* 2012:116.
 25. Rahpeyma A, Khajehahmadi S, Khalife HH. Decellularized human Schneiderian membrane: Electron microscopic study as a bioscaffold and preliminary cell seeding. *Pathology-Research and Practice.* 2014;210(12):965-70.
 26. Lin P, Chan WC, Badylak SF, Bhatia SN. Assessing porcine liver-derived biomatrix for hepatic tissue engineering. *Tissue engineering.* 2004;10(7-8):1046-53.
 27. Wallis JM, Borg ZD, Daly AB, Deng B, Ballif BA, Allen GB, et al. Comparative assessment of detergent-based protocols for mouse lung de-cellularization and re-cellularization. *Tissue Engineering Part C: Methods.* 2012;18(6):420-32.
 28. Badylak SF, Freytes DO, Gilbert TW. Extracellular matrix as a biological scaffold material: structure and function. *Acta biomaterialia.* 2009;5(1):1-13.
 29. Remlinger NT, Czajka CA, Juhas ME, Vorp DA, Stolz DB, Badylak SF, et al. Hydrated xenogeneic decellularized tracheal matrix as a scaffold for tracheal reconstruction. *Biomaterials.* 2010;31(13):3520-6.
 30. Dong X, Wei X, Yi W, Gu C, Kang X, Liu Y, et al. RGD-modified acellular bovine pericardium as a bioprosthetic scaffold for tissue engineering. *Journal of Materials Science: Materials in Medicine.* 2009;20(11):2327-36.
 31. Keane TJ, Londono R, Turner NJ, Badylak SF. Consequences of ineffective decellularization of biologic scaffolds on the host response. *Biomaterials.* 2012;33(6):1771-81.
 32. Brown B, Lindberg K, Reing J, Stolz DB, Badylak SF. The basement membrane component of biologic scaffolds derived from extracellular matrix. *Tissue engineering.* 2006;12(3):519-26.
 33. Hodde J, Record R, Tullius R, Badylak S. Fibronectin peptides mediate HMEC adhesion to porcine-derived extracellular matrix. *Biomaterials.* 2002;23(8):1841-8.
 34. Hodde J, Record R, Liang H, Badylak S. Vascular endothelial growth factor in porcine-derived extracellular matrix. *Endothelium.* 2001;8(1):11-24.
 35. Voytik-Harbin SL, Brightman AO, Kraine MR, Waisner B, Badylak SF. Identification of extractable growth factors from small intestinal submucosa. *Journal of cellular biochemistry.* 1997;67(4):478-91.
 36. Freytes DO, Badylak SF, Webster TJ, Geddes LA, Rundell AE. Biaxial strength of multilaminated extracellular matrix scaffolds. *Biomaterials.* 2004;25(12):2353-61.
 37. Hodde J, Hiles M. Virus safety of a porcine-derived medical device: Evaluation of a viral inactivation method. *Biotechnology and bioengineering.* 2002;79(2):211-6.
 38. Pruss A, Kao M, Kiesewetter H, Von Versen R, Pauli G. Virus safety of avital bone tissue transplants: evaluation of sterilization steps of spongiosa cuboids using a peracetic acid-methanol mixture. *Biologicals.* 1999;27(3):195-201.
 39. Badylak SF, Record R, Lindberg K, Hodde J, Park K. Small intestinal submucosa: a substrate for in vitro cell growth. *Journal of Biomaterials Science, Polymer Edition.* 1998;9(8):863-78.
 40. Badylak SF, Tullius R, Kokini K, Shelbourne KD, Klootwyk T, Voytik SL, et al. The use of xenogeneic small intestinal submucosa as a biomaterial for Achilles's tendon repair in a dog model. *Journal of biomedical materials research.* 1995;29(8):977-85.
 41. Hodde JP, Badylak SF, Brightman AO, Voytik-Harbin SL. Glycosaminoglycan content of small intestinal submucosa: a bioscaffold for tissue replacement. *Tissue engineering.* 1996;2(3):209-17.
 42. Prasertsung I, Kanokpanont S, Bunaprasert T, Thanakit V, Damrongsakkul S. Development of acellular dermis from porcine skin using periodic pressurized technique. *Journal of Biomedical Materials Research Part B: Applied Biomaterials.* 2008;85(1):210-9.
 43. Reing JE, Brown BN, Daly KA, Freund JM, Gilbert TW, Hsiong SX, et al. The effects of processing methods upon mechanical and biologic properties of porcine dermal extracellular matrix scaffolds. *Biomaterials.* 2010;31(33):8626-33.
 44. Gorschewsky O, Puetz A, Riechert K, Klakow A, Becker R. Quantitative analysis of biochemical characteristics of bone-patellar tendon-bone allografts. *Bio-medical materials and engineering.* 2005;15(6):403-11.
 45. Vyavahare N, Hirsch D, Lerner E, Baskin JZ, Schoen FJ, Bianco R, et al. Prevention of bioprosthetic heart valve calcification by ethanol preincubation efficacy and mechanisms. *Circulation.* 1997;95(2):479-88.
 46. Goissis G, Suzigan S, Parreira DR, Maniglia JV, Braile DM, Raymundo S. Preparation and Characterization of Collagen-Elastin Matrices From Blood Vessels Intended as Small Diameter Vascular Grafts. *Artificial organs.* 2000;24(3):217-23.
 47. Woods T, Gratzer PF. Effectiveness of three extraction techniques in the development of a decellularized bone-anterior cruciate ligament-bone graft. *Biomaterials.* 2005;26(35):7339-49.
 48. Dahl SL, Koh J, Prabhakar V, Niklason LE. Decellularized native and engineered arterial scaffolds for transplantation. *Cell transplantation.* 2003;12(6):659-66.
 49. Cox B, Emili A. Tissue subcellular fractionation and protein extraction for use in mass-spectrometry-based proteomics. *Nature protocols.* 2006;1(4):1872-8.
 50. Xu CC, Chan RW, Tirunagari N. A biodegradable, acellular xenogeneic scaffold for regeneration of

- the vocal fold lamina propria. *Tissue engineering*. 2007;13(3):551-66.
51. Rosario DJ, Reilly GC, Ali Salah E, Glover M, Bullock AJ, MacNeil S. Decellularization and sterilization of porcine urinary bladder matrix for tissue engineering in the lower urinary tract. 2008.
52. Ozeki M, Narita Y, Kagami H, Ohmiya N, Itoh A, Hirooka Y, et al. Evaluation of decellularized esophagus as a scaffold for cultured esophageal epithelial cells. *Journal of Biomedical Materials Research Part A*. 2006;79(4):771-8.
53. Zhou J, Fritze O, Schleicher M, Wendel H-P, Schenke-Layland K, Harasztosi C, et al. Impact of heart valve decellularization on 3-D ultrastructure, immunogenicity and thrombogenicity. *Biomaterials*. 2010;31(9):2549-54.
54. Flynn L. The use of decellularized adipose tissue to provide an inductive microenvironment for the adipogenic differentiation of human adipose-derived stem cells. *Biomaterials*. 2010;31(17):4715-24.
55. Brown BN, Freund JM, Han L, Rubin JP, Reing JE, Jeffries EM, et al. Comparison of three methods for the derivation of a biologic scaffold composed of adipose tissue extracellular matrix. *Tissue Engineering Part C: Methods*. 2011;17(4):411-21.
56. Levy RJ, Vyavahare N, Ogle M, Ashworth P, Bianco R, Schoen FJ. Inhibition of cusp and aortic wall calcification in ethanol-and aluminum-treated bioprosthetic heart valves in sheep: background, mechanisms, and synergism. *The Journal of heart valve disease*. 2003;12(2):209-16; discussion 16.
57. Gorschewsky O, Klakow A, Riechert K, Pitzl M, Becker R. Clinical comparison of the tutoplast allograft and autologous patellar tendon (bone-patellar tendon-bone) for the reconstruction of the anterior cruciate ligament 2-and 6-year results. *The American journal of sports medicine*. 2005;33(8):1202-9.
58. Wicha MS, Lowrie G, Kohn E, Bagavandoss P, Mahn T. Extracellular matrix promotes mammary epithelial growth and differentiation in vitro. *Proceedings of the National Academy of Sciences*. 1982;79(10):3213-7.
59. Lumpkins SB, Pierre N, McFetridge PS. A mechanical evaluation of three decellularization methods in the design of a xenogeneic scaffold for tissue engineering the temporomandibular joint disc. *Acta Biomaterialia*. 2008;4(4):808-16.
60. Montoya CV, McFetridge PS. Preparation of ex vivo-based biomaterials using convective flow decellularization. *Tissue Engineering Part C: Methods*. 2009;15(2):191-200.
61. Clark JN, Ogle MF, Ashworth P, Bianco RW, Levy RJ. Prevention of calcification of bioprosthetic heart valve cusp and aortic wall with ethanol and aluminum chloride. *The Annals of thoracic surgery*. 2005;79(3):897-904.
62. Luche S, Santoni V, Rabilloud T. Evaluation of non-ionic and zwitterionic detergents as membrane protein solubilizers in two-dimensional electrophoresis. *Proteomics*. 2003;3(3):249-53.
63. Kury F, Schneeberger C, Sliutz G, Kubista E, Salzer H, Medl M, et al. Determination of HER-2/neu amplification and expression in tumor tissue and cultured cells using a simple, phenol free method for nucleic acid isolation. *Oncogene*. 1990;5(9):1403-8.
64. Wang B, Tedder ME, Perez CE, Wang G, de Jongh Curry AL, To F, et al. Structural and biomechanical characterizations of porcine myocardial extracellular matrix. *Journal of Materials Science: Materials in Medicine*. 2012;23(8):1835-47.
65. Nakayama KH, Batchelder CA, Lee CI, Tarantal AF. Decellularized rhesus monkey kidney as a three-dimensional scaffold for renal tissue engineering. *Tissue Engineering Part A*. 2010;16(7):2207-16.
66. Du L, Wu X, Pang K, Yang Y. Histological evaluation and biomechanical characterisation of an acellular porcine cornea scaffold. *British Journal of Ophthalmology*. 2010;bjo. 2008.142539.
67. Funamoto S, Nam K, Kimura T, Murakoshi A, Hashimoto Y, Niwaya K, et al. The use of high-hydrostatic pressure treatment to decellularize blood vessels. *Biomaterials*. 2010;31(13):3590-5.
68. Keane TJ, Swinehart IT, Badylak SF. Methods of tissue decellularization used for preparation of biologic scaffolds and in vivo relevance. *Methods*. 2015;84:25-34.
69. Deeken C, White A, Bachman S, Ramshaw B, Cleveland D, Loy T, et al. Method of preparing a decellularized porcine tendon using tributyl phosphate. *Journal of Biomedical Materials Research Part B: Applied Biomaterials*. 2011;96(2):199-206.
70. Ott HC, Clippinger B, Conrad C, Schuetz C, Pomerantseva I, Ikonomou L, et al. Regeneration and orthotopic transplantation of a bioartificial lung. *Nature medicine*. 2010;16(8):927-33.
71. Krejčí J. Interaction of mixture of anionic surfactants with collagen. *International journal of cosmetic science*. 2007;29(2):121-9.
72. Greffrath SP, Reynolds JA. The molecular weight of the major glycoprotein from the human erythrocyte membrane. *Proceedings of the National Academy of Sciences*. 1974;71(10):3913-6.
73. Elder BD, Kim DH, Athanasiou KA. Developing an articular cartilage decellularization process toward facet joint cartilage replacement. *Neurosurgery*. 2010;66(4):722-7; discussion 7.
74. Hudson TW, Zawko S, Deister C, Lundy S, Hu CY, Lee K, et al. Optimized acellular nerve graft is immunologically tolerated and supports regeneration. *Tissue engineering*. 2004;10(11-12):1641-51.
75. Mallik AS, Fichter MA, Rieder S, Bilic G, Stergioula S, Henke J, et al. Fetoscopic closure of punctured fetal membranes with acellular human amnion plugs in a rabbit model. *Obstetrics & Gynecology*. 2007;110(5):1121-9.
76. Rieder E, Kasimir M-T, Silberhumer G, Seebacher G, Wolner E, Simon P, et al. Decellularization protocols of porcine heart valves differ importantly in efficien-

- cy of cell removal and susceptibility of the matrix to recellularization with human vascular cells. The Journal of thoracic and cardiovascular surgery. 2004;127(2):399-405.
77. Ketchedjian A, Jones AL, Krueger P, Robinson E, Crouch K, Wolfenbarger L, et al. Recellularization of decellularized allograft scaffolds in ovine great vessel reconstructions. The Annals of thoracic surgery. 2005;79(3):888-96.
 78. Price AP, England KA, Matson AM, Blazar BR, Panoskaltsis-Mortari A. Development of a decellularized lung bioreactor system for bioengineering the lung: the matrix reloaded. Tissue engineering Part A. 2010;16(8):2581-91.
 79. Yang M, Chen CZ, Wang XN, Zhu YB, Gu YJ. Favorable effects of the detergent and enzyme extraction method for preparing decellularized bovine pericardium scaffold for tissue engineered heart valves. Journal of Biomedical Materials Research Part B: Applied Biomaterials. 2009;91(1):354-61.
 80. Conconi MT, De Coppi P, Bellini S, Zara G, Sabatti M, Marzaro M, et al. Homologous muscle acellular matrix seeded with autologous myoblasts as a tissue-engineering approach to abdominal wall-defect repair. Biomaterials. 2005;26(15):2567-74.
 81. Seddon AM, Curnow P, Booth PJ. Membrane proteins, lipids and detergents: not just a soap opera. Biochimica et Biophysica Acta (BBA)-Biomembranes. 2004;1666(1):105-17.
 82. Baptista PM, Vyas D, Soker S. Liver Regeneration and Bioengineering-The Emergence of Whole Organ Scaffolds: INTECH Open Access Publisher; 2012.
 83. Baptista PM, Orlando G, Mirmalek-Sani S-H, Siddiqui M, Atala A, Soker S, editors. Whole organ decellularization-a tool for bioscaffold fabrication and organ bioengineering. 2009 Annual International Conference of the IEEE Engineering in Medicine and Biology Society; 2009: IEEE.
 84. Baptista PM, Siddiqui MM, Lozier G, Rodriguez SR, Atala A, Soker S. The use of whole organ decellularization for the generation of a vascularized liver organoid. Hepatology. 2011;53(2):604-17.
 85. Mendoza-Novelo B, Avila EE, Cauich-Rodríguez JV, Jorge-Herrero E, Rojo FJ, Guinea GV, et al. Decellularization of pericardial tissue and its impact on tensile viscoelasticity and glycosaminoglycan content. Acta biomaterialia. 2011;7(3):1241-8.
 86. Song JJ, Kim SS, Liu Z, Madsen JC, Mathisen DJ, Vacanti JP, et al. Enhanced in vivo function of bioartificial lungs in rats. The Annals of thoracic surgery. 2011;92(3):998-1006.
 87. Jensen T, Roszell B, Zang F, Girard E, Matson A, Thrall R, et al. A rapid lung de-cellularization protocol supports embryonic stem cell differentiation in vitro and following implantation. Tissue Engineering Part C: Methods. 2012;18(8):632-46.
 88. Neel EAA, Chrzanowski W, Salih VM, Kim H-W, Knowles JC. Tissue engineering in dentistry. Journal of dentistry. 2014;42(8):915-28.
 89. Kolker AR, Brown DJ, Redstone JS, Scarpinato VM, Wallack MK. Multilayer reconstruction of abdominal wall defects with acellular dermal allograft (AlloDerm) and component separation. Annals of plastic surgery. 2005;55(1):36-42.
 90. Grauss RW, Hazekamp MG, van Vliet S, Gittenberger-de Groot AC, DeRuiter MC. Decellularization of rat aortic valve allografts reduces leaflet destruction and extracellular matrix remodeling. J Thorac Cardiovasc Surg. 2003;126(6):2003-10.
 91. Grauss RW, Hazekamp MG, Oppenhuizen F, van Munsteren CJ, Gittenberger-de Groot AC, DeRuiter MC. Histological evaluation of decellularised porcine aortic valves: matrix changes due to different decellularisation methods. European journal of cardio-thoracic surgery : official journal of the European Association for Cardio-thoracic Surgery. 2005;27(4):566-71.
 92. Bader A, Steinhoff G, Strobl K, Schilling T, Brandes G, Mertsching H, et al. Engineering of human vascular aortic tissue based on a xenogeneic starter matrix. Transplantation. 2000;70(1):7-14.
 93. Cebotari S, Tudorache I, Jaekel T, Hilfiker A, Dorfman S, Ternes W, et al. Detergent decellularization of heart valves for tissue engineering: toxicological effects of residual detergents on human endothelial cells. Artificial organs. 2010;34(3):206-10.
 94. Feil G, Christ-Adler M, Maurer S, Corvin S, Rennekampff H-O, Krug J, et al. Investigations of urothelial cells seeded on commercially available small intestine submucosa. European urology. 2006;50(6):1330-7.
 95. Petersen TH, Calle EA, Zhao L, Lee EJ, Gui L, Raredon MB, et al. Tissue-engineered lungs for in vivo implantation. Science. 2010;329(5991):538-41.
 96. Gui L, Chan SA, Breuer CK, Niklason LE. Novel utilization of serum in tissue decellularization. Tissue Engineering Part C: Methods. 2009;16(2):173-84.
 97. Schenke-Layland K, Vasilevski O, Opitz F, König K, Riemann I, Halbhuber K, et al. Impact of decellularization of xenogeneic tissue on extracellular matrix integrity for tissue engineering of heart valves. Journal of structural biology. 2003;143(3):201-8.
 98. Moore R, Madara J, MacLeod R. Enterocytes adhere preferentially to collagen IV in a differentially regulated divalent cation-dependent manner. American Journal of Physiology-Gastrointestinal and Liver Physiology. 1994;266(6):G1099-G107.
 99. Gailit J, Ruoslahti E. Regulation of the fibronectin receptor affinity by divalent cations. Journal of Biological Chemistry. 1988;263(26):12927-32.
 100. Klebe RJ. Cell Attachment to collagen: The requirement for energy. Journal of cellular physiology. 1975;86(2):231-6.
 101. Lehr EJ, Rayat GR, Chiu B, Churchill T, McGann LE, Coe JY, et al. Decellularization reduces immunogenicity of sheep pulmonary artery vascular patches. The Journal of thoracic and cardiovascular surgery. 2011;141(4):1056-62.
 102. Yang B, Zhang Y, Zhou L, Sun Z, Zheng J, Chen Y, et al. Development of a porcine bladder acellular ma-

- trix with well-preserved extracellular bioactive factors for tissue engineering. *Tissue Engineering Part C: Methods*. 2010;16(5):1201-11.
103. Meyer SR, Chiu B, Churchill TA, Zhu L, Lakey JR, Ross DB. Comparison of aortic valve allograft decellularization techniques in the rat. *Journal of biomedical materials research Part A*. 2006;79(2):254-62.
104. Hopkinson A, Shanmuganathan VA, Gray T, Yeung AM, Lowe J, James DK, et al. Optimization of amniotic membrane (AM) denuding for tissue engineering. *Tissue Engineering Part C: Methods*. 2008;14(4):371-81.
105. Atala A. Tissue engineering, stem cells and cloning: current concepts and changing trends. *Expert opinion on biological therapy*. 2005;5(7):879-92.
106. Gouk SS, Lim TM, Teoh SH, Sun WQ. Alterations of human acellular tissue matrix by gamma irradiation: histology, biomechanical property, stability, in vitro cell repopulation, and remodeling. *Journal of Biomedical Materials Research Part B: Applied Biomaterials*. 2008;84(1):205-17.
107. Nagata S, Hanayama R, Kawane K. Autoimmunity and the clearance of dead cells. *Cell*. 2010;140(5):619-30.
108. Kakkar R, Suruchi, Grover R. Theoretical study of molecular recognition by Hoechst 33258 derivatives. *Journal of Biomolecular Structure and Dynamics*. 2005;23(1):37-47.
109. Conklin B, Richter E, Kreutziger K, Zhong D-S, Chen C. Development and evaluation of a novel decellularized vascular xenograft. *Medical engineering & physics*. 2002;24(3):173-83.
110. Quintana JR, Lipanov AA, Dickerson RE. Low-temperature crystallographic analyses of the binding of Hoechst 33258 to the double-helical DNA dodecamer CGCGAATTCGCG. *Biochemistry*. 1991;30(42):10294-306.
111. Ahn SJ, Costa J, Emanuel JR. PicoGreen quantitation of DNA: effective evaluation of samples pre-or post-PCR. *Nucleic acids research*. 1996;24(13):2623-5.
112. Lotfi B, Mehranjani MS, Mahdizadeh M. Simultaneous effect of green tea catechin and bisphenol A on differentiation of bone marrow mesenchymal stem cells to osteoblast in vitro. *Journal of Kermanshah University of Medical Sciences (J Kermanshah Univ Med Sci)*. 2014;18(9):498-508.